

## $\mathsf{inShiCel} \mathbb{R}$

GinShiCel MH 9336-X3 is a high viscosity, unmodified water solution Description:

cellulose ether made for cementitious building materials. It improves

the consistency, stability, and water retention.

**Specifications** 

2% Viscosity (RV@20 Celsius)

55000 ~ 65000 cps

Appearance:

Whitish powder

Particle size:

99% < 250 microns

**Moisture Content** Ash Content

Max 5% Max 6%

**Applications** 

**Suggested Applications** 

Cementitious Tile Adhesives, manual plaster, skim coat plaster

Packaging and Storage

Woven multi-layer bags with Polyethylene lining Bags

Net weight: 25KG

**Pallets** 4 bags per layer, total 13

layers Net weight 1300 KG

Containers 20 ft General Purpose container: 13000 KG, 10 pallets

40 ft General Purpose container: 26000 KG, 20 pallets

Other congiguration possible upon inquiry

In unopened bags, this product can last several years. In opened bags, the Storage

> moisture content of this product will be influenced by air humidity. See MSDS for information on handling, transportation, and storage of the

product.

No representation or warranty, expressed or implied, is made as to the accuracy or completeness of the information or data contained herein and producer shall have no obligation or liability whatsoever with respect to any such information or data, including, but not limited to, any liability for infringement of patent or other industrial property rights. Producer disclaims all implied warranties of merchantability and tness for a particular purpose. Producer shall in no event be liable for incidental or consequential damages, including, without limitation, lost profit, loss of income, loss of business opportunity and any other related costs and expenses.